

## High Temperature Lubricating Vacuum Grease, Inert

July 2014

Page 1 of 2

### Description


Apiezon PFPE 501 is a high performance lubricant and sealant which can be used with confidence in extreme environments, ultra high vacuum conditions and in the presence of gaseous and liquid oxygen at elevated temperatures.

The branched perfluoropolyether base oil and PTFE thickener facilitate the grease's excellent lubricity and chemical inertness across its temperature range. In harsh environments PFPE 501 can be relied upon to perform up to 250°C in the presence of a range of aggressive chemicals including halogens, alkalis, fuels, corrosives and fuming nitric acid.

Being extremely resistant to solvents it is ideal for use in coating, semiconductor and other industries where aggressive chemicals and strong oxidising agents are regularly used.

### Advantages of using PFPE 501

- ▶ **Robust** - Chemical inertness and oxidation stability make PFPE 501 ideal under the most extreme operating conditions.
- ▶ **Safe & Reliable** - Non-toxic, non-flammable and maintains lubricity and thermal stability up to 250°C.
- ▶ **Extends Service Life** - Branched PFPE structure and double-density provides film-forming and superior load-carrying capability.
- ▶ **Versatile** - Used in a wide range of applications including bearings, valves, gears, threads, o-rings and seals.




### Ultra High Vacuum

The extremely low vapour pressure characteristics of PFPE 501 (as demonstrated in the graph below) ensure the grease can be used with confidence under ultra high vacuum conditions.

### Cleaning

Wipe off excess grease with a lint-free cloth. Residual grease can be removed using a perfluorinated solvent. For stringent cleanliness a further stage using acetone is recommended.



### Compatibility


Apiezon PFPE 501 is compatible with all types of material including plastics, metals, ceramics, polymers, elastomers ethers, alcohols and hydrocarbons.

At elevated temperatures it is recommended to avoid contact with Lewis acid catalysts such as aluminium chloride, boron trifluoride, titanium tetrachloride and newly exposed rubbing surfaces of aluminium, magnesium or titanium alloys.

PFPE 501 is compatible with all chemicals, corrosives and solvents except those with a perfluorinated base.

### Vapour pressure over working temperature range

Vapour Pressure, Torr



## High Temperature Lubricating Vacuum Grease, Inert

July 2014

Page 2 of 2

### Shelf life

The shelf life of Apiezon PFPE 501 is four years from date of manufacture, providing the product is in the original unopened packaging and has been stored at ambient (10 to 30°C) temperature.

### Typical Properties

<i>NLGI No.</i>		2
<i>Penetration P60</i>		280
<i>Typical working temperature range</i>	°C	-15 to 250
	°F	5 to 482
<i>Vapour pressure @ 25°C / 77°F, Torr</i>		$1.3 \times 10^{-12}$
<i>Relative density @ 25°C / 77°F</i>		2.003
<i>4 ball weld point (load), kg - ASTM D2596</i>		800
<i>4 ball wear scar, mm - ASTM D2266 (40kg)</i>		0.94
<i>Outgassing characteristics - ASTM.E 595-90</i>		
<i>TML</i>		<1%
<i>CVCM</i>		<0.1%
<i>Evaporation 24hrs @ 100°C / 212°F</i>		0.02%
<i>Oil separation 24hrs @ 100°C / 212°F</i>		2.10%
<i>Low temperature torque, g/cm</i>		
<i>25°C / 77°F Starting</i>		162.3
<i>25°C / 77°F Running</i>		64.4

All properties quoted in this table are typical values and do not constitute a specification.